



AN EASY DOSE RATE GUIDE FOR THE USE OF 'abilox[®]' PIGMENTS IN PRE-MIXED CONCRETE

FOR A DOSE RATE OF **8.3%**

ABILITY BUILDING COLOURS
Subsidiary of Australian Oxides Pty Ltd
133-135 Northern Road, West Heidelberg, Vic, 3081, Australia
Tel: (03) 9457 6488 Fax: (03) 9458 4683

'abilox[®]'
BLACK CAF-X2
Sample Biscuit
Dose Rate: 8.3% in
off-white cement (by weight) (110)

INDICATION OF CURED SHADE ONLY.
IN PRACTISE FINAL SHADE TAKES TYPICALLY 28 DAYS TO ACHIEVE

Email: service@abilityproducts.com.au

You will need to purchase/order/specify abilox[®] by weight of the concretes cementitious binder weight as a percentage:
8.3% equals:

Two (2) x 12.5kg bags per cubic metre of 25 MPa strength concrete

PLEASE NOTE:
IN THE ABILITY 'COLOUR SPECIFIER' WHICH SHOWS THE abilox[®] COLOURS @ 8.3% AND 4.15%

'gc' means: grey cement
'owc' means: off white cement

PLEASE NOTE:
On the 'biscuit' label it specifies what type of cement needs to be used: either grey cement or off-white cement

ABILITY BUILDING COLOURS
Subsidiary of Australian Oxides Pty Ltd
133-135 Northern Road, West Heidelberg, Vic, 3081, Australia
Tel: (03) 9457 6488 Fax: (03) 9458 4683

'abilox[®]'
BLACK CAF-X2
Sample Biscuit
Dose Rate: 8.3% in
grey cement (by weight) (5)

INDICATION OF CURED SHADE ONLY.
IN PRACTISE FINAL SHADE TAKES TYPICALLY 28 DAYS TO ACHIEVE

Email: service@abilityproducts.com.au

FOR A DOSE RATE OF **4.15%**

ABILITY BUILDING COLOURS
Subsidiary of Australian Oxides Pty Ltd
133-135 Northern Road, West Heidelberg, Vic, 3081, Australia
Tel: (03) 9457 6488 Fax: (03) 9458 4683

'abilox[®]'
BLACK CAF-X2
Sample Biscuit
Dose Rate: 4.14% in
off-white cement (by weight) (111)

INDICATION OF CURED SHADE ONLY.
IN PRACTISE FINAL SHADE TAKES TYPICALLY 28 DAYS TO ACHIEVE

Email: service@abilityproducts.com.au

You will need to purchase/order/specify abilox[®] by weight of the concretes cementitious binder weight as a percentage:
4.15% equals:

One (1) x 12.5kg bag per cubic metre of 25 MPa strength concrete

PLEASE NOTE:
IN THE ABILITY 'COLOUR SPECIFIER' WHICH SHOWS THE abilox[®] COLOURS @ 8.3% AND 4.15%

'gc' means: grey cement
'owc' means: off white cement

PLEASE NOTE:
On the 'biscuit' label it specifies what type of cement needs to be used: either grey cement or off-white cement

ABILITY BUILDING COLOURS
Subsidiary of Australian Oxides Pty Ltd
133-135 Northern Road, West Heidelberg, Vic, 3081, Australia
Tel: (03) 9457 6488 Fax: (03) 9458 4683

'abilox[®]'
BLACK CAF-X2
Sample Biscuit
Dose Rate: 4.15% in
grey cement (by weight) (6)

INDICATION OF CURED SHADE ONLY.
IN PRACTISE FINAL SHADE TAKES TYPICALLY 28 DAYS TO ACHIEVE

Email: service@abilityproducts.com.au